


| <b>19 x 7 RR</b>   |           |                                 |                                 |
|--|-----------|---------------------------------|---------------------------------|
| <b>Rope Diameter</b>   |           | <b>Approx. Weight (lb./ft.)</b> | <b>Nominal Strength (tons)*</b> |
| <b>Inches</b>  | <b>MM</b> |                                 |                                 |
| 3/16   | 4.8       | 0.064                           | 1.57                            |
| 1/4  | 6.5       | 0.113                           | 2.77                            |
| 5/16   | 8.0       | 0.177                           | 4.30                            |
| 3/8  | 9.5       | 0.250                           | 6.15                            |
| 7/16   | 11        | 0.350                           | 8.33                            |
| 1/2  | 13        | 0.450                           | 10.8                            |
| 9/16   | 14.5      | 0.580                           | 13.6                            |
| 5/8  | 16        | 0.710                           | 16.8                            |
| 3/4  | 19        | 1.020                           | 24.0                            |
| 7/8  | 22        | 1.390                           | 32.5                            |
| 1  | 26        | 1.820                           | 42.2                            |
| 1-1/8  | 29        | 2.300                           | 53.1                            |
| 1-1/4  | 32        | 2.840                           | 65.1                            |
| 1-3/8  | 35        | 3.430                           | 78.4                            |
| 1-1/2  | 38        | 4.080                           | 92.8                            |
|                                 |           |                                 |                                 |
| <b>19 x 7 RR</b>   |           |                                 |                                 |
| <p>(Note*) = Acceptance strength is not less than 2-1/2% below the normal strengths listed. Tons of 2,000 lbs.</p> |           |                                 |                                 |